

TRANSPROP™ HSCUT-F

DESCRIPTION:

TransProp™ HSCUT-F is a clear biaxially oriented polypropylene film, corona treated one side and heat sealable two side. One side has a reduced heat seal threshold. **(Also available in 120 and 160 gauge)**

CHARACTERISTICS:

- Excellent transparency and print receptivity
- Heat sealable on both sides
- Reduced heat seal threshold on non-treated side
- Standard moisture barrier
- Good antistatic and slip properties

FDA STATUS:

Manufactured with materials compliant with FDA regulations.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUES				TEST METHOD
Thickness	Gauge	60	72	80	100	-
Yield	in ² /lb	51,643	43,047	38,675	31,000	-
Tensile Strength MD	lb/in ²	17,404	17,404	17,404	17,404	ASTM D 882
Tensile Strength TD	lb/in ²	29,007	29,007	29,007	29,007	ASTM D 882
Elongation at Break MD	%	≤180	≤180	≤180	≤180	ASTM D 882
Elongation at Break TD	%	≤70	≤70	≤70	≤70	ASTM D 882
Haze	%	≤1.7	≤1.7	≤1.7	≤1.7	ASTM D 1003
Gloss (60°)	%	≥90	≥90	≥90	≥90	ASTM D 2457
Thermal shrinkage MD	°F	≤4.0	≤4.0	≤4.0	≤4.0	266°F, 5 min.
Thermal shrinkage TD	°F	≤2.0	≤2.0	≤2.0	≤2.0	266°F, 5 min.
Heat seal range – non-treated side	°F	221-293	221-293	221-293	221-293	QB/T2358-1998
Heat seal range – treated side	°F	239-293	239-293	239-293	239-293	QB/T2358-1998
Sealing strength	psi	≥1.14	≥1.14	≥1.14	≥1.14	QB/T2358-1998
C.O.F – non-treated side		≤0.25	≤0.25	≤0.25	≤0.25	ASTM D1894
C.O.F – treated side		≤0.25	≤0.25	≤0.25	≤0.25	ASTM D1894
Surface tension – treated side	Dyne	≥38	≥38	≥38	≥38	QB/T14216-2008
WVTR	g/in ² /day	1.47	1.32	1.16	.93	ASTM F1249 (100°F,90% RH)

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 10/24/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM