

TRANSCELLO™ KHB20-F

DESCRIPTION:

Transcello KHB20-F is a regenerated cellulose film, coated on both sides with a PVDC coating.

CHARACTERISTICS:

- Inbuilt jaw release properties on both sides
- Excellent barrier to water vapor, gases, and aromas
- Excellent dead-fold characteristics
- Resistant to oils and greases
- Heat sealable on both sides
- Anti-static
- Both sides of the film are receptive to inks, adhesives and tear tapes
- Biodegradable base film
- High gloss and transparency

FDA STATUS:

Manufactured with materials compliant with FDA regulations.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE				TEST METHOD
Thickness	Gauge	76	86	100	137	-
Yield	in ² /lb	25,100	22,300	19,300	14,100	-
Tensile Strength MD	psi	18,000	18,000	18,000	18,000	ASTM D882
Tensile Strength TD	psi	10,000	10,000	10,000	10,000	ASTM D882
Elongation at Break MD	%	22	22	22	22	ASTM D882
Elongation at Break TD	%	70	70	70	70	ASTM D882
Seal Strength	g(f)in	225	225	225	225	275°F; 0.5 secs; 6psi
WVTR	g/100 in ² /24 hrs	0.65	0.65	0.65	0.65	ASTM E96 100°F 90% RH
OTR	cc/100 in ² /24 hrs	0.19	0.19	0.19	0.19	ASTM D1927 75°F 0% RH
Gloss 45°	Units	105	105	105	105	ASTM D2457
Haze (wide angle) 2.5°	%	4	4	4	4	ASTM D1003
Sealing range	°F	210-320	210-320	210-320	210-320	0.5 secs; 10 psi
COF	Static	0.25	0.25	0.25	0.25	ASTM D1894
COF	Dynamic	0.20	0.20	0.20	0.20	ASTM D1894

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 9/29/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2016 Transcendia Inc. All Rights Reserved.