

NATUREFLEX® NM-F

DESCRIPTION

Natureflex NM-F is a two-side barrier coated, one side metalized compostable film.

CHARACTERISTICS

- Based on renewable resources
- Certified as compostable in both industrial and home composting environments, also suitable for anaerobic digestion
- Excellent barrier to moisture and UV/visible light
- Formulated for ease of conversion with enhanced print receptivity
- Ultra-high luster and sparkle
- Controlled slip characteristics
- Heat sealable on non-metalized side
- Cold seal compatible
- Excellent dead-fold characteristics
- Inherent anti-static properties
- Excellent barrier to gases and aromas
- Resistant to oils and greases

FDA STATUS

Manufactured with materials compliant with FDA regulations.

COMPLIANCE

Please visit <https://www.transcendia.com/compliance> for more compliance information.

TECHNICAL DATA

PROPERTIES		UNIT OF MEASURE	TYPICAL VALUE		TEST METHOD
Thickness		gauge	92	118	-
Yield		in ² /lb	21,000	16,400	-
Tensile Strength	MD	psi	18,000		ASTM D882
Tensile Strength	TD	psi	10,000		ASTM D882
Elongation at Break	MD	%	22		ASTM D882
Elongation at Break	TD	%	70		ASTM D882
1% Secant modulus	MD	psi	>170,000		ASTM D882
1% Secant modulus	TD	psi	>85,000		ASTM D882
Seal Strength		g(f)/in	200		275°F, 0.5 secs, 10psi
Optical Density		-	2.5		-
CoF, met/met (Dynamic)		-	0.40		ASTM D1894
CoF, non-met/non-met (Dynamic)		-	0.30		ASTM D1894
WVTR (100°F, 90% RH)		g/100 in ² /day	0.65		ASTM E96
OTR (73°F, 50% RH)		cc/100 in ² /day	0.06		ASTM D1927

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
TRANSCENDIA.COM

Revision Date: 1/8/224
 ©2024 Transcendia Inc. All Rights Reserved