

TRANS-CLING™ II Low Tack Vinyl (PVC)

DESCRIPTION

TRANS-CLING II Low Tack Vinyl (PVC) film has a low-tack pressure sensitive adhesive for use on smooth surfaces. It is available in a white matte or a clear gloss surface.

CHARACTERISTICS

- Can be applied to most clean, non-porous surfaces
- Withstands many weather conditions
- Temperature ranges from -40°F to 180°F

FDA STATUS

Manufactured with materials compliant with FDA regulations.

COMPLIANCE

Please visit <https://www.transcendia.com/compliance> for more compliance information.

TECHNICAL DATA

PROPERTIES	CLEAR POLISHED	WHITE
Thickness-Tolerance is $\pm$ 5% or .001 whichever is greatest	4.8 to 5.2 mil with adhesive.	
Printing	Material suitable for screen process, offset lithography, and flexography	
Dimensional Stability	Good	
Min. Application Temperature	+50°F	
Exterior Exposure	Test for U.V. discolor under extreme conditions	
Adhesion	Glass – 6 to 16 oz./in. Removable up to 1 year on interior applications and 6 months on exterior applications	
Water & Humidity Resistance	Fair, slight haze will develop in high humidity conditions and will clear when normal humidity returns. Immersion not recommended	
Shelf Life	2 years when stored at 74°F and 50% relative humidity	

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
TRANSCENDIA.COM

Revision Date: 1/14/2025
 ©2025 Transcendia Inc. All Rights Reserved