

Mylar® OL12AF

DESCRIPTION

Mylar OL12AF-F is a biaxially oriented polyester film with an amorphous polyester heat seal layer. It has an anti-fogging capability to provide better clarity when stored and displayed in refrigerated conditions.

CHARACTERISTICS

- Dual ovenable
- Strong, aggressive seals to APET, PETG, CPET, Polyester-coated paperboard and PVC
- Can be used in hot fill applications
- Self-venting
- Excellent grease and oil resistance
- Can withstand freezing temperatures down to -40°F and heating up to 400°F
- May be hard to peel without shredding

FDA STATUS

Manufactured with materials compliant with FDA regulations

COMPLIANCE

Please visit transcendia.com/compliance for more compliance information.

TECHNICAL DATA

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE			TEST METHOD
Thickness	Gauge	50	100	150	-
Yield	in ² /lb	30,800	18,400	12,500	-
Tensile Strength MD at break	psi	25,000	25,000	25,000	ASTM D882A
Tensile Strength TD at break	psi	35,000	35,000	35,000	ASTM D882A
Elongation at Break MD	%	110	110	110	ASTM D882A
Elongation at Break TD	%	80	80	80	ASTM D882A
Gas Permeability O ₂ , 24 hr	cc/100in ²	9	5	3	ASTM D3985 22°C/75% RH/1 ATM
WVTR	g/100 in ² /day	2.8	1.3	0.9	ASTM F1249 38°C, 90% RH
Tear (Graves)	lb	0.7	1.1	1.3	ASTM D1004

These values are typical performance data for DuPont Mylar films.

Mylar® is a registered trademark of DuPont® Teijin® Films for its polyester films. Only DuPont Teijin Films makes Mylar®.

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM