

## TRANSPAQUE® II Polypropylene (PP) Film

### DESCRIPTION

TRANSPAQUE II is a block-out opaque polypropylene (PP) film for both indoor and outdoor banner applications.

### CHARACTERISTICS

- Corona treated for 2-sided printing
- Good layflat characteristics
- Exceptional tear resistance
- Easy to sew, grommet and fold
- Outdoor life expectancy is one year
- Higher yield than PVC banner films
- Easy to print using a variety of methods including UV Lithography, UV Digital and UV Screen Printing
- Available in sheets and rolls

### COMPLIANCE

Please visit [transcendia.com/compliance](http://transcendia.com/compliance) for more compliance information.

### TECHNICAL DATA

Physical Properties		Unit of Measure	Typical Values			Test Method
Thickness		mil.	8	9	13	TRANSCENDIA Test
Yield		in <sup>2</sup> /lb.	3,342	2,970	2,056	TRANSCENDIA Test
Opacity (Block Out)		%	>100	>100	>100	ASTM D1003
Tensile Strength at Break	MD	psi	3,100	3,100	3,100	ASTM D882
	TD		2,900	2,900	2,900	
Elongation at Break	MD	%	>400	>400	>400	ASTM D882
	TD		>400	>400	>400	
Gloss	Inside, Gardner @ 60°	%	26	26	26	TRANSCENDIA Test
	Outside, Gardner @ 60°		32	32	32	
Heat Shrinkage, 212°F/10 min.		%	Nil	Nil	Nil	

\*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

#### CORPORATE HEADQUARTERS

USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax  
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

[TRANSCENDIA.COM](http://TRANSCENDIA.COM)

Revision Date: 5/28/2026  
 ©2026 Transcendia Inc. All Rights Reserved