



TRANSPET™ AF/AG

DESCRIPTION:

TransPet AF/AG is a clear polyester film coated on both sides for Anti-fog and Anti-glare performance.

• Typical applications include disposable face shields, visors, and other temporary optical and industrial uses.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Thickness	Gauge	450	-
Yield	in²/lb	4410	-
LTL	%	96	ASTM D1003
Haze	%	0.90	ASTM D1003
Tensile Strength MD	psi	22,000	ASTM D882A
Tensile Strength TD	psi	24,000	ASTM D882A
Shrinkage MD	%	2.5	190°C x 5 min unrestrained
Shrinkage TD	%	1.0	190°C x 5 min unrestrained

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 9/28/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131 USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM