

TRANSCENDIA® CWFCT-F

DESCRIPTION:

CWFCT-F is a white cavitated biaxially oriented polypropylene film. It is non heat-sealable with a high energy flame treatment on one side and a corona treatment on the opposite side.

CHARACTERISTICS:

- High opacity
- High energy flame treated for excellent ink adhesion and adhesive and extrusion lamination
- Excellent flatness

COMPLIANCE:

Please visit transcendia.com/compliance for more compliance information.

FDA STATUS:

Manufactured with materials compliant with FDA regulations

TECHNICAL DATA

PROPERTIES	UNIT OF MEASURE	TECHNICAL DATA				TEST METHOD
Thickness	Gauge	100	115	152	217	-
Yield	in ² /lb	44,000	38,400	27,800	19,500	-
Opacity	%	76	82	88	93	ASTM D589
Tensile Strength MD	psi	10,000				ASTM D882
Tensile Strength TD	psi	20,000				ASTM D882
Elongation at Break MD	%	110				ASTM D882
Elongation at Break TD	%	50				ASTM D882
Dimensional Stability MD	%	<5				266°F/5min
Dimensional Stability TD	%	<3				266°F/5min
Surface Energy (Flame Side)	dyne/cm	38				ASTM D2578
Surface Energy (Corona Side)	dyne/cm	36				ASTM D2578

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
[TRANSCENDIA.COM](https://transcendia.com)

Revision Date: 5/1/2023
 ©2023 Transcendia Inc. All Rights Reserved