

# TRANSPROP™ HS1CW-F

## DESCRIPTION:

TransProp HS1CW-F is a white gloss white cavitated polypropylene film, one side sealable and opposite side treated.

## CHARACTERISTICS:

- Very wide heat seal range
- 39% yield advantage over white opaque films
- Low and consistent COF
- Very high puncture resistance
- Good moisture and odor barrier

## FDA STATUS:

Manufactured with materials compliant with FDA regulations.

## TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE	TEST METHOD
Thickness	Gauge	169	-
Yield	in <sup>2</sup> /lb.	23,500	-
Breaking Load MD	Lbs/in	20.6	-
Breaking Load TD	Lbs/in	46.8	-
Elongation at Break MD	%	140	ASTM D882
Elongation at Break TD	%	35	ASTM D882
COF	%	0.27	-
WVTR	g/100in <sup>2</sup> /24h	0.28	ASTM F 1249 100°F 90% RH
Opacity	%	85	ASTM D1003
Gloss (45°)	G.U.	50	ASTM D2457
Heat Seal Strength	g/in	173	185°F/14.5psi/0.5 sec
Heat Seal Range	°F (min-max)	175-300	
Surface Tension	Dyne/cm	36-39	ASTM D2578

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date:9/29/2016

**CORPORATE HEADQUARTERS** 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

**TRANSCENDIA.COM**