

DIGIKote[®] Hard Coat Textured Laminating Film

DESCRIPTION:

DIGIKote[®] Hard Coat Textured is a low melt, thermally activated laminate which is top coated with a UV cured hard coat formula designed to offer maximum scuff and scratch resistance. The film offers excellent glare reduction and aesthetic appeal under bright light conditions. It is ideal for trade show graphics and point of purchase displays that require extra durability.

CHARACTERISTICS:

- Low-melt-point adhesive.
- Scuff and scratch resistance
- Non-reflective surface.
- Water, oil, acid, and alkali resistant.
- Can be die cut.

Slit Widths Available: 5 mil – 38”, 43”, 51” / 10 mil – 25”, 38”, 51”

Length Available: 5 and 10 mil – 250’

TECHNICAL DATA:

PROPERTIES				ASTM
THICKNESS + 10%		.005	.010	
SURFACE TENSION - dyne - adhesive side		52 to 54		
COEFFICIENT OF FRICTION OF BASE FILM SIDE		0.4 to 0.5		D 1894
TENSILE STRENGTH - psi + 10%	MD	16,200	18,900	D 882
	TD	18,600	21,700	
ELONGATION - %	MD	115		D 882
	TD	80		
YIELD - in./lb.		4,570	2,200	
LAMINATING TEMPERATURE RANGE – °F – Internal		185° to 195°		
BOND STRENGTH - p/i - laminated to itself		12	15	

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the “Information”) shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser’s reliance on the Information.

Revision Date: 9/29/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM