

TRANSPROP™ MOPPWC

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Thickness	Gauge	300	-
Yield	in ² /lb.	10,359	-
Tensile Strength MD	psi	35,534	DIN EN ISO 527
Tensile Stress at 10% strain MD	psi	15,374	DIN EN ISO 527
Tensile Strain at Break MD	%	50 - 60	DIN EN ISO 527
Opacity	%	5.3	-
Shrinkage MD (257°F/10 min)	%	4.0	DIN EN ISO 11501

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 10/24/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2016 Transcendia Inc. All Rights Reserved.