

TransMD® PCH-120

DESCRIPTION:

PCH-120 – 92 ga. PET / 3 mil LDPE

CHARACTERISTICS:

- Packaging material suitable for healthcare products
- Very good puncture and abrasion resistance
- Commonly used in medical pouch fabrication
- Used with peelable films or itself for non-peelable seal

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE	TEST METHOD
Thickness	in	.0039	-
Yield	in ² /lb	6,850	-
Tensile Strength MD	psi	6,335	ASTM D882
Tensile Strength TD	psi	6,655	ASTM D882
Elongation at Break MD	%	90	ASTM D882
Elongation at Break TD	%	80	ASTM D882
Seal Strength to itself, 300°F, 50 psi, 1 sec dwell		DESTRUCT	ASTM F88

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 10/24/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2016 Transcendia Inc. All Rights Reserved.