

ProPrint® - XLR

DESCRIPTION:

ProPrint® – XLR is a synthetic paper that has Xceptional printability, is the Latest technology that facilitates product degradation in a biologically active waste stream and is a Responsible alternative when materials are not being recycled.

ProPrint® – XLR is an engineered extruded mineral filled polypropylene. This specialized formula is available in white opaque with a matte/matte or gloss/matte finish.

Characteristics:

- Easily printed using offset lithography, UV Digital, gravure, flexography and screen printing
- Can be folded, hot stamped, embossed, die cut, riveted, stapled and sewn
- Great for indoor and outdoor applications
- Excellent dimensional stability
- Tough and has good impact strength
- Characteristics allow for deep draw forming
- Better mold shape transferal and fast cycle times
- ISO 9001:2015 Certified Quality Management Systems

Available thicknesses: Rolls 6 mil to 20 mil

Sheets 10 mil to 60 mil

TECHNICAL DATA:

PROPERTIES	UNIT	TYPICAL VALUES		TEST METHOD
THICKNESS ± 5% or .001 Maximum (whichever is greater)	inches	.010	.015	T 411
GRAMMAGE BASIS WEIGHT	g / m ²	276	414	T 410
YIELD	in ² / lb	2600	1725	
SPECIFIC GRAVITY	g/cm ³	1.05	1.05	D 1505
TENSILE STRENGTH @ BREAK	MD	psi	3400	D 882
	TD		3000	
ELONGATION @ BREAK	MD	%	550	
	TD		500	
TEAR RESISTANCE INITIATED	MD	lb	1	D 1938
	TD		4	
TEAR RESISTANCE UNINITIATED	MD	lb	6.4	D 1004
	TD		8	
UNNOTCHED IZOD IMPACT*		NO BREAKS	NO BREAKS	D256A
WETTING TENSION - minimum	Corona Treated	dynes/cm	40	T698
	Non Corona treated		34	
STIFFNESS	MD	Taber Units	10	D 5342
	TD		13	
HDT @ 264 psi*	° F	145		D 648

* indicates data was obtained from molded samples only, in an unannealed state.

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own tests. Transilwrap shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision 02/19/2021

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL

60131 USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM