

TRANSPROP™ SMFCTL-F

DESCRIPTION:

TransProp™ SMFCTL-F is a clear non-heat sealable biaxially oriented polypropylene film, high energy treated one side and corona treated, slip modified on the opposite side.

CHARACTERISTICS:

- High energy flame treatment provides excellent ink adhesion and adhesive and extrusion lamination bonds
- Superior Optical Properties
- Commonly used in roll-fed bottle label applications, laminated to itself or to cavitated white polypropylene
- Outer web of film/film, film/paper and film/PE laminations
- Excellent flatness

FDA STATUS:

Manufactured with materials compliant with FDA regulations.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUES					TEST METHOD
		60	70	75	100	120	
Thickness	Gauge	60	70	75	100	120	-
Yield	in ² /lb	51,800	44,000	41,100	31,400	25,700	-
Tensile Strength MD	lb/in ²	20,000	20,000	20,000	20,000	20,000	ASTM D 882
Tensile Strength TD	lb/in ²	32,000	32,000	32,000	32,000	32,000	ASTM D 882
Elongation at Break MD	%	140	140	140	140	140	ASTM D 882
Elongation at Break TD	%	60	60	60	60	60	ASTM D 882
COF (corona treat side)	Dynamic	0.20	0.20	0.20	0.20	0.20	ASTM D 1894
COF (corona treat side)	Static	0.25	0.25	0.25	0.25	0.25	ASTM D 1894
Haze	%	2.0	2.0	2.0	2.0	2.0	ASTM D 1003
Gloss (45°)	G.U.	90	90	90	90	90	ASTM D 2457
WVTR	g/100in ² /24hr	0.50	0.45	0.40	0.30	0.20	ASTM F 1249 100°F 90% RH
Dimensional Stability MD	%	<5	<5	<5	<5	<5	266°F, 5 min.
Dimensional Stability TD	%	<3	<3	<3	<3	<3	266°F, 5 min.
Surface Energy (High Energy Flame Side)	dyne/cm	40	40	40	40	40	ASTM D 2578
Surface Energy (Corona Treated Side)	dyne/cm	36	36	36	36	36	ASTM D 2578

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 09/20/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2016 Transcendia Inc. All Rights Reserved.