

TransPaque® II

DESCRIPTION:

TransPaque-II is a block-out opaque polyolefin film for both indoor and outdoor banner applications.

Characteristics:

- Corona treated for 2 sided printing
- Good Lay Flat characteristics
- Exceptional Tear resistance
- Easy to print using a variety of methods including UV Lithography, UV Digital and UV Screen Printing
- Easy to sew, grommet and fold
- Outdoor life expectancy is one year.
- Higher yield than PVC banner films
- Available in Sheets and Rolls
- Recycle code #5

TECHNICAL DATA :

Physical Properties	Unit of Measure	Typical Values *			Test Method
Thickness		8 mil	9 mil	13 mil	TRANSCENDIA Test
Yield	in ² /lb	3,342	2,970	2,056	TRANSCENDIA Test
Opacity (Block Out)	%	>100	>100	>100	ASTM D1003
Tensile Strength at Break	MD	3,100	3,100	3,100	ASTM D882
	TD	2,900	2,900	2,900	
Elongation at Break	MD	>400	>400	>400	ASTM D882
	TD	>400	>400	>400	
Gloss Inside, Gardner @ 60°	%	26	26	26	TRANSCENDIA Test
Gloss Outside, Gardner @ 60°		32	32	32	
Heat Shrinkage 212°F/10 min	%	Nil	Nil	Nil	

*Values given as typical and should not interpreted as product specifications. All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own tests. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 09/22/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2016 Transcendia Inc. All Rights Reserved.