

# Transalloy® P-260EX Multi-Polymer Alloy

## DESCRIPTION:

Transalloy® P-260EX is a multi-polymer material formulated for durability, high tear resistance and excellent impact strength for the most demanding applications. It offers a medium range of rigidity and is often used as a PVC alternative in some applications. Transalloy® P-260EX can be used in point of purchase displays, in-store signage, outdoor displays, horticultural signage/tags, thermoformed trays and promotional items.

## CHARACTERISTICS:

- Can be printed Offset Lithography, Screen, UV Digital and Flexography
- Can be heat bent, hot or cold folded, die cut, thermoformed and guillotine cut
- Excellent dimensional stability
- Provides good toughness and impact strength
- Available in sheets or rolls
- Available in a variety of opacities from natural to dead opaque
- Corona treatment or UV Inhibitors available upon request
- Surfaces include satin/matte, ultra gloss/matte
- Recycle Code #6

## TECHNICAL DATA:

PROPERTIES	UNIT	TYPICAL VALUES	TEST METHOD
THICKNESS ± 5% or .001 Maximum (whichever is greater)	inches	.010" TO .050"	T 411
YIELD @ .020	ln <sup>2</sup> / lb	1300	T410
SPECIFIC GRAVITY @ .020	g/cm <sup>3</sup>	1.03	D 1505
TENSILE STRENGTH @ .020 @ BREAK	MD	3300	D 882
	TD	2800	
ELONGATION @ .020 @ BREAK	MD	135%	
	TD	150%	
TEAR RESISTANCE @ .020 INITIATED	MD	.9	D 1938
	TD	1.4	
TEAR RESISTANCE @ .020 UNINITIATED	MD	7.0	D 1004
	TD	7.4	
STIFFNESS @ .020	MD	98	
	TD	109	
WETTING TENSION - minimum	Dyne/cm <sup>2</sup>	45	T698

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 10/25/2016

**CORPORATE HEADQUARTERS** 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

[TRANSCENDIA.COM](http://TRANSCENDIA.COM)

© 2016 Transcendia Inc. All Rights Reserved.