

TRANS KOTE® EL-4/3 MR

DESCRIPTION:

TRANS KOTE® EL-4/3 MR is a 7 mil polyester film with adhesive, designed for single side lamination. It features elevated dielectric strength.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	PROPERTY VALUE	TEST METHOD
Thickness	Gauge	700 ± 5% (total) ; 393.7 ± 4% (PET only)	-
Yield	in ² /lb	3,310	-
Tensile Strength MD	psi	15,700	ASTM D882
Tensile Strength TD	psi	17,100	ASTM D882
Elongation at Break MD	%	175	ASTM D882
Elongation at Break TD	%	130	ASTM D882
Dielectric Strength (4 mil PET)	kV	15 Avg (Minimum = 12.5)	ASTM D149 (60hz, AC)

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 08/29/2017

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2017 Transcendia Inc. All Rights Reserved.