

TRANS-KOTE® 2/3 EL PET/MR

DESCRIPTION:

TRANS-KOTE® 2/3 EL PET/MR is a heavy gauge, high clarity polyester based film designed for single side lamination. It features elevated dielectric strength.

TECHNICAL DATA:

PROPERTY	UNIT OF MEASURE	PROPERTY VALUE	TEST METHOD
Thickness	Gauge	500 +/- 5% total	-
Yield	in ² /lb	4,910	ASTM D882
Tensile Strength MD	psi	12,200	ASTM D882
Tensile Strength TD	psi	13,200	ASTM D882
Elongation at Break MD	%	145	ASTM D882
Elongation at Break TD	%	120	ASTM D882
Dielectric Strength (2 mil PET)	kV	Avg. 11 (Minimum = 9)	ASTM D149 (60hz, AC)
Laminating Temperature Range – Roll Lamination	F°	210-230	-

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 01/25/2018

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.321-8544 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

© 2018 Transcendia Inc. All Rights Reserved.