

# TRANS-KOTE® EL 3/3 MR

## DESCRIPTION:

TRANS-KOTE® EL 3/3 MR is a 6 mil polyester film with adhesive, designed for single side lamination. It features elevated dielectric strength.

## TECHNICAL DATA:

PROPERTY	UNIT OF MEASURE	PROPERTY VALUE	TEST METHOD
Thickness PET ONLY	Gauge	600 +/- 5% 293 +/- 4%	-
Yield	in <sup>2</sup> /lb	3970	ASTM D882
Tensile Strength MD	psi	14,000	ASTM D882
Tensile Strength TD	psi	15,000	ASTM D882
Elongation at Break MD	%	160	ASTM D882
Elongation at Break TD	%	110	ASTM D882
Dielectric Strength (3 mil PET)	kV	Avg. 13.4 (Minimum = 10.2)	ASTM D149 (60hz, AC)
Laminating Temperature Range – Roll Lamination	F°	210-230	-

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 02/20/2018