




TRANS-SEALING® MBL75-F

DESCRIPTION:

TRANS-SEALING® MBL75-F is a PA/PE lamination for medium barrier Lidding applications and use with Vertical Form Fill Seal (VFFS) equipment.

CHARACTERISTICS:

- Flexible
- Excellent heat sealing properties that can be sealed to different substrates such as PE, PP, PS, and PVC
- Various gauges and widths available
- PA provides good puncture resistance and high and low temperature resistance



FDA STATUS:

Manufactured with materials compliant with FDA, KOSHER, CFIA, and QS regulations for direct food contact applications.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Thickness	Gauge	300	-
Yield	in²/lb	9300	-
Tensile Strength MD	psi	7540	ASTM D882
Tensile Strength TD	psi	7540	ASTM D882
Elongation at Break MD	%	58	ASTM D882
Elongation at Break TD	%	58	ASTM D882
COF		0.2	ASTM D1894
O ₂ TR	cc/100 in².d.bar@65% RH & 73 F	4.0	ASTM D3985
WVTR	g/100 in²/day	0.45	ASTMF1249
Seal Strength	lbf/in	10.0	ASTMF2029
Bond Strength	N/0.6in	1.2	GB/T 8808-88
Residual Solvent	Mg/in²	0.0035	GB/T 10004-08

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 08/09/2017

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131 **USA** 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax