

TRANSPET® GPLH-F

DESCRIPTION:

TRANSPET® GPLH-F is an untreated slightly rough-surfaced and hazy polyester film for enhanced handling and runability. **(Also available in 400, 752, and 1000 gauge).**

FDA STATUS:

Manufactured with materials compliant with FDA regulations.

TECHNICAL DATA:

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE						TEST METHOD
		92	142	200	300	500	700	
Thickness	Gauge	92	142	200	300	500	700	-
Yield	in ² /lbs.	21,911	13,950	10,044	6679	4015	2868	-
Coefficient of Friction	Kinetic	0.30 - 0.32	0.30 - 0.32	0.30 - 0.32	0.30	0.30	0.30	ASTM D1894
Coefficient of Friction	Static	0.37-0.40	0.37 - 0.40	0.37 - 0.40	0.4	0.40	0.35	ASTM D1894
Tensile Strength MD	psi	30,000-35,000	30,000-33,000	29,500-33,000	30,000	28,600	27,200	ASTM D882
Tensile Strength TD	psi	31,500	31,400-33,400	31,400 - 37,500	31,400	30,000	28,600	ASTM D882
Elongation at Break MD	%	140	140 - 150	140 - 165	140	150	150	ASTM D882
Elongation at Break TD	%	120 - 130	120 - 130	120 - 130	130	140	130	ASTM D882
Haze	%	3.8 - 5.0	4.8 - 6.0	6.0 - 7.0	8.0	12	15	ASTM D1003
TLT	%	89.3	89.1	89.0	88.4	87.8	-	ASTM D1003
Heat Shrinkage MD	%	1.6	1.5 - 1.6	1.4 - 2.5	1.4	1.2	1.0	30 min at 150°C
Heat Shrinkage TD	%	0.2 - 1.5	0.2 - 0.6	0.2 - 0.8	0.2	0.2	0.6	30 min at 150°C
Gloss	%	160	157.5	157	-	-	-	ASTM D 523
Surface Tension	Dyne	45	45	45	45	-	-	ASTM D2578

All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

Revision Date: 9/20/2016

CORPORATE HEADQUARTERS 9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.618.5060 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM